

## Certificate of Analysis

Consulting Engineers  
and Geoscientists

### Adhesion to Asphalt

|                  |  |
|------------------|--|
| Product Name     | Streetbond SP-150  |
| Batch Number     | ResinA: #93937, Colorant: Brick #93461; CatalystB: #93938  |
| Manufacture Date | 2/07/02  |
| Sample Prep Date | 3/08/02  |
| Testing Date(s)  | 3/15/02  |
| Test Method      | ASTM D-4541 Standard Test Method for Pull-Off Strength of Coatings Using Portable Adhesion Testers |
| Test Conditions  | As per ASTM standard. Any deviation reported at end of certificate.                                |


This certificate confirms that the above product was tested as per stated standard specification using calibrated equipment and qualified staff. The following test results were obtained.

#### Test Results

| Substrate   | Mpa  | lb./sq.in. | location of failure |
|---|------|------------|---------------------|
| 3/8" Unpolished-Asphalt                           | 1.43 | 208        | **                  |
| 3/8" Polished-Asphalt                             | 1.15 | 167        | **                  |
| 3/4" Unpolished-Asphalt                           | 1.83 | 266        | **                  |
| 3/4" Polished-Asphalt                             | 2.36 | 342        | **                  |
| * Combination Asphalt Cohesive / Coating Adhesive |      |            |                     |
| **Asphalt Cohesive                                |      |            |                     |

|   |
|---|
| <b>Test conditions (if different from standard test conditions) and/or notes:</b>         |
| Coatings cured at 23°C. / 22% RH for one week   |
| Unpolished asphalt surface is the untouched surface of the asphalt disc(fresh asphalt)    |
| Polished asphalt surface is the cut surface and is intended to simulate aged asphalt.     |
| Utilized Positest Portable Pull-Off Adhesion Tester (Type II) device and aluminum dollies |
| Results are the average of three trials.  |

GeoEngineers - Gifford, Inc.

  
Timothy D. Barber

GeoEngineers, Inc.  
523 East 2nd Avenue  
Spokane, WA 99202  
Telephone (509) 363-3125  
Fax (509) 363-3126